



GRIZZLYGREASE No. 1 MG

OG P F 0 N -30



Date of issue: 14.09.2020

GRIZZLY GREASE No. 1 MG is a lubricant for open gears and contains thermally stable solid lubricants.

GRIZZLYGREASE No. 1 MG is based on lithium/calcium complex with high pressure additives, which are combined with the soap structure so that an optimum adhesiveness to the metal surface is possible.

Special properties

- Remarkable adhesive properties
- Excellent high load carrying capacity
- High resistance to temperature
- Excellent corrosion and wear protection
- High resistance to water

Product Characteristics	Value	Dimension	Norm / Standard
Colour	anthracite		
Density at 20°C	0,95	g/cm ³	DIN 51757
Operating temperature range	-30 to 150	°C	
Thickener	Li / Ca special soap		
Base oil	Mineral oil		
Kin. viscosity of the base oil at 40°C	800	mm ² /s	DIN EN ISO 3104
Kin. viscosity of the base oil at 100°C	40	mm ² /s	DIN EN ISO 3104
Worked penetration	355 – 385	mm/10	DIN ISO 2137
Consistency class (NLGI)	0		DIN 51818
Dropping point	> 220	°C	DIN ISO 2176
Resistance to water	0 – 90		DIN 51807
Corrosion protection (SKF-Emcor)	0 / 0		DIN 51802
FZG-test A/2,76/50	> 12		DIN 51354
Four-ball welded load	> 7800	N	DIN 51350

Application

GRIZZLY GREASE No. 1 MG had been developed as special grease for high loaded open gears such as ore mills. Due to the high temperature properties **GRIZZLY GREASE No. 1 MG** can be used for a wide range of applications, where high temperatures and high loads exist. **GRIZZLY GREASE No. 1 MG** can be recommended for ball bearings and roller bearings as well as for slide bearings/bushes.

Packaging units

25 kg hobbock, 50 kg hobbock, 180 kg drum



The products are subject to continuous strict production controls and comply with our own factory specifications. A warranty for each case cannot be given, due to the variety of relevant factors. Therefore, we recommend the implementation of field tests. Herewith, any liability is expressly excluded.

LUBRICANT CONSULT GMBH · Gutenbergstrasse 13 · 63477 Maintal (Germany)
Tel: +49 (0) 6109 / 7650-0 · Fax: +49 (0) 6109 / 7650-51 · E-Mail: webmaster@lubcon.com · Internet: <http://www.lubcon.com>