



# TURMOGREASE LC 802 EP

K P HC 2/3 N -30



Date of issue: 07.02.2019

**TURMOGREASE LC 802 EP** is a multipurpose long-term lubricant for different requirements.

**TURMOGREASE LC 802 EP** is a grease consisting of lithium-calcium soap, a special base oil and additives in order to optimize lubricant properties.

### Special properties

- Excellent corrosion and wear protection
- High load carrying capacity and excellent EP-characteristics
- Good media resistance
- Resistant against separation and constant oil delivery
- Excellent nonferrous metal protection and aging protection
- Good adhesive properties
- Good water resistance
- High lubricating film stability

Product Characteristics	Value	Dimension	Norm / Standard
Colour	beige		
Density at 20°C	0,88	g/cm <sup>3</sup>	DIN 51757
Operating temperature range	-35 to 140	°C	
Thickener	Li / Ca special soap		
Base oil	Synth. HC / Mineral oil		
Kin. viscosity of the base oil at 40°C	82	mm <sup>2</sup> /s	DIN EN ISO 3104
Kin. viscosity of the base oil at 100°C	12,5	mm <sup>2</sup> /s	DIN EN ISO 3104
Worked penetration	250 - 275	mm/10	DIN ISO 2137
Consistency class (NLGI)	2 – 3		DIN 51818
Dropping point	> 180	°C	DIN ISO 2176
Resistance to water	0 – 90		DIN 51807
Corrosion protection (SKF-Empcor)	0 / 0		DIN 51802
Speed factor of grease (n x dm)	1 000 000	mm/min	

### Application

Lubrication of rolling and sliding bearings for low and high temperatures. Universal grease for automobiles and commercial vehicles as well as for the entire machine building industry.

### Packaging units

20 x 400 g cartridges, 6 x 1 kg cans, 5 kg bucket, 25 kg hobbock, 180 kg drum



The products are subject to continuous strict production controls and comply with our own factory specifications. A warranty for each case cannot be given, due to the variety of relevant factors. Therefore, we recommend the implementation of field tests. Herewith, any liability is expressly excluded.

LUBRICANT CONSULT GMBH · Gutenbergstrasse 13 · 63477 Maintal (Germany)  
Tel: +49 (0) 6109 / 7650-0 · Fax: +49 (0) 6109 / 7650-51 · E-Mail: [webmaster@lubcon.com](mailto:webmaster@lubcon.com) · Internet: <http://www.lubcon.com>