



TURMOTEMPOIL 400/02



Date of issue: 24.10.2019

TURMOTEMPOIL 400/02 is a special oil based on perfluorinated polyether.

Therefore **TURMOTEMPOIL 400/02** belongs to the thermally and chemically most stable lubricants. It is used successfully, if operating temperatures and chemical influences exclude the use of conventional lubricants.

TURMOTEMPOIL 400/02 is NSF H1 registered as lubricant for which an incidental contact with food technically cannot be avoided.

Special properties

- High thermal stability and oxidation resistance
- High resistance to chemicals
- High load carrying capacity
- Residue-free evaporation
- Non-combustible
- No swelling of plastomers and elastomers

Product Characteristics	Value	Dimension	Norm / Standard
Colour	colourless		
Density at 20°C	1,9	g/cm ³	DIN 51757
Operating temperature range	to 200	°C	
Kinematic viscosity at 40°C	89	mm ² /s	DIN EN ISO 3104
Kinematic viscosity at 100°C	11	mm ² /s	DIN EN ISO 3104
Viscosity index (VI)	109		DIN ISO 2909
Pour point	-35	°C	DIN ISO 3016
Flash point	not inflammable	°C	DIN EN ISO 2592

Application

TURMOTEMPOIL 400/02 is used in the precision mechanic and optical industry, in the electrotechnical industry and the general machine building industry.

Prior to the initial lubrication with **TURMOTEMPOIL 400/02** it is mandatory to clean surfaces thoroughly. Optimum lubricating properties can only be fully achieved on clean and dry material surfaces.

At operating temperatures above 260°C, aggressive decomposition products (e.g. hydrofluoric acid) can form.

Packaging units

100 ml bottle, 1 l bottle, 5 l canister



126462



The products are subject to continuous strict production controls and comply with our own factory specifications. A warranty for each case cannot be given, due to the variety of relevant factors. Therefore, we recommend the implementation of field tests. Herewith, any liability is expressly excluded.

LUBRICANT CONSULT GMBH · Gutenbergstrasse 13 · 63477 Maintal (Germany)
Tel: +49 (0) 6109 / 7650-0 · Fax: +49 (0) 6109 / 7650-51 · E-Mail: webmaster@lubcon.com · Internet: <http://www.lubcon.com>